

SPECIAL FORCES



VINY NITRILE EXAMINATION GLOVES POWDER FREE

ASTM D6319

Physical Dimensions		
Glove Length (mm)	≥ 230	
Palm Thickness (mm)	0.09 ± 0.02	
Finger Thickness (mm)	0.12 ± 0.02	
Physical Properties		
Test	Before Aging	After Aging
Tensile strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 500	≥ 400

EN455

Physical Dimensions		
Median glove length (mm)	≥240	
Median Palm Thickness (mm)	0.09 ± 0.02	
Median Finger Thickness (mm)	0.12 ± 0.02	
Physical Properties		
Test	Before Aging	After Aging
Median Force at break (mm)	≥ 6	≥ 6

Regulatory compliance

FDA 510(K) MDD 93/42/EEC REACH ROHS Directive
2002/95/EC PPE89/686/EEC

Standards

ASTM D6319, ASTM 6978, EN 455 Part 1,2,3,4 EN420,
EN374 Part 1, 2 & 3

Classification

Class 1 (FDA), Class1 (MDD 93/42/EEC), Category III (PPE
89/686/EEC)



Application Setting

Medium risk - medical, dental, procedures, chemotherapy drugs,
pathology lab, patientcare, and food handling

Colour

Aqua Blue, BLACK

